



FOAMULAR® C-300

Extruded Polystyrene (XPS)

Rigid Foam Board Insulation



PRODUCT FEATURES

Description

Extruded polystyrene (XPS) rigid insulation board with thermal and moisture resistive properties.

Basic Uses/Related Uses

Continuous insulation for use on residential and commercial above and below grade wall assemblies and suitable under floor slabs that do not exceed 30 psi.

Selection Criteria

- Thermal resistance of R5 per inch[†]
- Moisture resistant (hydrophobic), long term durability
- Compatible with common liquid or sheet applied air/moisture barriers

Sustainability Criteria

- Recycled content of 20%, pre-consumer (SCS Global Services)
- UL GREENGUARD Gold Certification
- Product specific Type 4 UL Environmental Product Declaration and Transparency Brief
- Silver Material Health Certification (Cradle to Cradle Products Innovation Institute)
- Contributes to credits in green building programs such as LEED® and Green Globes. For further information see documents: LEED® v4 for Building Design and Construction and Owens Corning Impact Study - Leadership in Energy and Environmental Design (LEED® v4).

Applicable Standards

CAN/ULC-S701	Standard for Thermal Insulation, Polystyrene Boards
CAN/ULC-S102.2	Standard Method of Test for Surface Burning Characteristics of Flooring, Floor Coverings and Miscellaneous Materials and Assemblies
ASTM C177	Standard Test Method for Steady-State Heat Flux Measurements and Thermal Transmission Properties by Means of the Guarded-Hot-Plate
ASTM C203	Standard Test Method for Breaking Load and Flexural Properties of Block-Type Thermal Insulation
ASTM C518	Standard Test Method for Steady-State Thermal Transmission Properties by Means of the Heat Flow Meter Apparatus
ASTM E228	Standard Test Method for Linear Thermal Expansion of Solid Materials with a Push-rod Dilatometer
ASTM D1621	Standard Test Method for Compressive Properties of Rigid Cellular Plastics
ASTM D2126	Standard Test Method for Response of Rigid Cellular Plastics to Thermal and Humid Aging
ASTM D2842	Standard Test Method for Water Absorption of Rigid Cellular Plastics
ASTM E96	Test Methods for Water Vapour Transmission of Materials

Performance Criteria

Compliance:	Evaluation Listing No. 13430-L Type 4	CCMC CAN/ULC-S701
Physical Properties:	Compressive Strength ¹ : 30 psi (210 kPa) Compressive Modulus: 1350 psi (9308 kPa) Flexural Strength: 75 psi (517 kPa) Dimensional Stability, Maximum, % linear change: 1.5 Linear Coefficient of Thermal Expansion: 3.5 x 10⁻⁵ in./in./°F (6.3 x 10⁻⁵ mm/mm/°C)	ASTM D1621 ASTM D1621 ASTM C203 ASTM D2126 ASTM E228
Thermal:	R5 ft ² hr°F/BTU per inch (RSI 0.88 m ² °C/W per 25 mm)	ASTM C518 or C177
Moisture:	Water Absorption, (max. % by volume): 0.70 Water Vapour Permeance: 0.87 Perm (50 ng/Pa.S.m²) Water Capillarity: None Water Affinity: Hydrophobic Limiting Oxygen Index, (min.): 24	ASTM D2842 ASTM E96 - ASTM D2863
Fire:	Combustible Max. Service Temp. 165 °F (74 °C)	CAN/ULC-S114 -

¹10% deformation or yield, whichever occurs first

Delivery and Storage

Deliver products in their original packages, and store in enclosed shelter. Packaging is not UV resistant. Shelter unused packages from the elements.

[†]The LTR performance for Owens Corning FOAMULAR® insulation products per CAN/ULC S701-17 are as follows:
Type 3 products: Minimum LTR of RSI 1.62 at 50 mm thickness & Type 4 products: minimum LTR of RSI 1.66 at 50 mm thickness. Please consult local Owens Corning Technical Representative.





FOAMULAR® C-300

Extruded Polystyrene (XPS)

Rigid Foam Board Insulation

Limitations

- Exposure to exterior conditions during normal construction cycles is permitted. During that time some fading of color may begin due to UV exposure, and, if exposed for extended periods of time, some degradation or “dusting” of the polystyrene surface may begin. It is best if the product is covered within 60 days to minimize degradation. Once covered, the deterioration stops, and damage is limited to the thin top surface layers of cells. Cells below are generally unharmed.
- This product is combustible. A protective barrier or thermal barrier is required to separate this product from interior living or conditioned spaces as specified in the appropriate building code.
- FOAMULAR® XPS insulation limited lifetime warranty maintains 90% of its thermal resistance for the lifetime of the building and covers all CAN/ULC- S701.
- Prior to use of adhesives, sealants or other similar products with polystyrene boards, verify their compatibility with adhesive manufacturers.

Sizes

Thickness	Widths	Lengths	Edges
FOAMULAR® C-300 XPS*			
25 mm - 102 mm (1" - 4") in 12.7 mm (1/2") increments	610 mm (24")	2438 mm (96")	Square or Ship Lapped

FOAMULAR® C-300 is shipped in units containing four individually shrink-wrapped packages.

*Metric sizes for CMU also available

Safety

This product is combustible and may constitute a fire risk if not used or installed properly. Although it contains a fire-suppressing agent, the product will ignite if exposed to a sufficiently intense flame. Do not expose to open flames or any other ignition source during transport, handling, storage or use. For additional information refer to Safe Use Instruction Sheet (SUIS) found in the SDS Database via <http://sds.owenscorning.com>.

PRODUCT PLACEMENT

Installation

Carefully adjust insulation boards to obtain tight joints between each board and around electrical service boxes, piping, air ducts and framing passing through; where two layers are required it is preferable to offset all joints. Consult an Owens Corning Canada Technical representative for appropriate fastener and adhesive selections.

Technical Services Available

For Canadian Technical inquiries please contact local representative. See Technical territory map via www.specowenscorning.ca/contacttech.

Current Ed: 2018.09.01
Previous Ed: 2018.09.01

Disclaimer of Liability

Technical information contained herein is furnished without charge or obligation and is given and accepted at recipient's sole risk. Because conditions of use may vary and are beyond our control, Owens Corning makes no representation about, and is not responsible or liable for the accuracy or reliability of data associated with particular uses of any product described herein.

SCS Global Services provides independent verification of recycled content in building materials and verifies recycled content claims made by manufacturers. For more information, visit www.SCSglobalservices.com.

LEED® is a registered trademark of the U.S. Green Building Council.



OWENS CORNING CANADA LP
3450 MCNICOLL AVENUE
SCARBOROUGH, ONTARIO M1V 1Z5
1-800-GET-PINK®
www.owenscorning.ca

Pub. No. 501120. Printed in Canada. September 2018.
THE PINK PANTHER™ & © 1964–2018 Metro-Goldwyn-Mayer Studios Inc.
All Rights Reserved. The colour PINK is a registered trademark of Owens Corning.
© 2018 Owens Corning. All Rights Reserved.

