



FOAMULAR® NGX™ 350 & 350 CVI

EXTRUDED POLYSTYRENE (XPS) RIGID FOAM INSULATION

Owens Corning® FOAMULAR® NGX™ 350 & 350 CVI Extruded Polystyrene (XPS) Insulations are closed-cell, moisture-resistant rigid foam boards with high compressive strength designed to be used in protected membrane roof assemblies. The 350 CVI product has drainage channels to facilitate water drainage in roofing assembly.

FOAMULAR® NGX™ 350 & 350 CVI contains the additional benefit of being manufactured with a blowing agent formulation that delivers a 90% reduction to Global Warming Potential (100 year), including the complete elimination of HFC 134a.¹

1. Compared to FOAMULAR® 350 & 350 CVI products.


Product Features



**SUPERIOR
MOISTURE
RESISTANCE**



DURABLE



**EASY TO CUT,
FORM & FIT**

Basic Uses/Related Uses

- Commercial flat roof assemblies

Selection Criteria

- Protected membrane roofing applications
- Drainage channels with CVI
- Tapered boards by 3rd party
- Thermal resistance of R5 per inch
- Moisture resistant (hydrophobic), long term durability
- Compatible with modified bituminous, hot applied liquid rubber, thermoplastic, and EPDM waterproofing membranes

Performance Criteria

COMPLIANCE:	CCMC Evaluation Listing No. 13430-L Type 4	CCMC CAN ULC S701.1-17
--------------------	---	---------------------------

Additional Performance Information

PHYSICAL PROPERTIES:	Compressive Strength ³ : 35 psi (240 kPa) Compressive Modulus (typical): 1480 (10204 kPa) Flexural Strength ⁴ (typical): 80 psi (552 kPa) Dimensional Stability, Maximum, % linear change: 1.5 Linear Coefficient of Thermal Expansion: 3.5 x 10⁻⁵ in./in./°F (6.3 x 10⁻⁵ mm/mm/°C)	ASTM D1621 ASTM D1621 ASTM C203 ASTM D2126 ASTM E228
THERMAL⁵:	Thermal Resistance, R-Value, hr-ft ² ·°F/Btu (RSI, °C·m ² /W) 5.0 (0.88) @ 24 °C (75 °F) mean temperature 5.4 (0.95) @ 4.4 °C (40 °F) mean temperature 5.6 (0.99) @ -3.9 °C (25 °F) mean temperature	ASTM C518 or C177
LTTR: (CANADA)	FOAMULAR® NGX™ Min. LTTR RSI (m ² °C/W) RSI: 0.86 @ 25.4 mm thickness RSI: 1.28 @ 38.1 mm thickness RSI: 1.70 @ 50.8 mm thickness RSI: 2.13 @ 63.5 mm thickness RSI: 2.59 @ 76.2 mm thickness RSI: 3.05 @ 88.9 mm thickness RSI: 3.52 @ 101.6 mm thickness	CAN ULC S770-15
MOISTURE:	Water Absorption, (max. % by volume): 0.30 Water Vapour Permeance (typical) FOAMULAR® NGX™: 0.3 Perms (17 ng/Pa.s.m²) Water Capillarity: None Water Affinity: Hydrophobic Limiting Oxygen Index, min.: 24	ASTM D2842 ASTM E96 - ASTM D2863
FIRE:	Combustible	CAN/ULC-S114
MAX. SERVICE TEMP.:	Max. Service Temp. 74 °C (165 °F)	-

3. Values at yield or 10% deflection, whichever occurs first.

4. Value at yield or 5%, whichever occurs first.

5. The R-value for FOAMULAR® NGX™ XPS Insulation is provided from testing at mean temperatures of: -3.9 °C (25 °F), 4.4 °C (40 °F), and 24 °C (75 °F) and aging techniques of 180-day real time aged (as mandated by ASTM C578).

Technical Information

- Deliver FOAMULAR® NGX™ XPS insulation products in their original factory-wrapped packaging.
- Exposure to exterior conditions during normal construction cycles is permitted. During that time some fading of color may begin due to UV exposure, and, if exposed for extended periods of time, some degradation or “dusting” of the polystyrene surface may begin. It is best if the product is covered within 60 days to minimize degradation. Once covered, the deterioration stops, and damage is limited to the thin top surface layers of cells. Cells below are generally unharmed.
- Prior to use of adhesives, sealants or other similar products with polystyrene boards, verify their compatibility with adhesive manufacturers.
- Caution: This product is combustible. A protective barrier or thermal barrier is required as specified in the appropriate building Code. Do not expose to open flames or any other ignition source during transport, handling, storage or use. A protective barrier or thermal barrier is required to separate this product from interior living or conditioned spaces as specified in the appropriate building code.
- Place and adjust FOAMULAR® NGX 350 or 350 CVI XPS insulation boards on the roof membrane to obtain tight joints or lapped with two thicknesses of insulation. Make tight joints between each board and around roof drains, air ducts and framing passing through; where two layers are required, overlap all joints. Once insulation boards are installed, cover completely with a filter fabric and ballast, gravel, soil, prefabricated pavers or other finishes, having the required weight. Consult an Owens Corning Canada Technical representative for appropriate fastener and adhesive selections.

Sizes


THICKNESS	WIDTHS	LENGTHS	EDGES
FOAMULAR® NGX™ 350 & 350 CVI XPS			
38 mm, 51 mm, 64 mm, 76 mm, 102 mm (1.5", 2", 2.5", 3", 4")	610 mm (24")	1220 mm (48")	Ship Lapped

FOAMULAR® NGX™ 350 or 350 CVI is shipped in units containing four individually shrink-wrapped packages.

350 CVI board contains one lengthwise and two widthwise grooves:
13 mm wide x 13 mm deep max. (0.5 in. x 0.5 in.). One entire perimeter groove
6.5 mm wide x 13 mm deep max. (0.25 in. x 0.5 in.).

Certifications and Sustainable Features

- Certified by SCS Global Services to contain a minimum of 20% recycled content pre-consumer
- GREENGUARD Certified products are certified to GREENGUARD standards for low chemical emissions into indoor air during product usage. For more information, visit ul.com/gg
- Product specific Type 4 UL Environmental Product Declaration (EPD) and Transparency Brief certified by UL Environment
- Contributes to credits in green building programs such as LEED® and Green Globes. For further information see documents: LEED® v4 for Building Design and Construction and Owens Corning Impact Study - Leadership in Energy and Environmental Design (LEED® v4)



Environmental and Sustainability

Owens Corning is a worldwide leader in building material systems, insulation and composite solutions, delivering a broad range of high-quality products and services. Owens Corning is committed to driving sustainability by delivering solutions, transforming markets and enhancing lives. More information can be found at www.owenscorning.ca or www.owenscorninglibrary.ca.

FOAMULAR® NGX™ is manufactured with a polystyrene resin and a blend of HFO and HFC blowing agents that have a global warming potential (100 year) of less than 80.

Disclaimer of Liability

Technical information contained herein is furnished without charge or obligation and is given and accepted at recipient's sole risk. Because conditions of use may vary and are beyond our control, Owens Corning makes no representation about and is not responsible or liable for the accuracy or reliability of data associated with particular uses of any product described herein. SCS Global Services provides independent verification of recycled content in building materials and verifies recycled content claims made by manufacturers. For more information, visit www.SCSglobalservices.com.

LEED® is a registered trademark of the U.S. Green Building Council.

Notes

For additional information, refer to the Safe Use Instruction Sheet (SUIS) found in the SDS Database via <http://sds.owenscorning.com>.

Limited Warranty

FOAMULAR® NGX™ XPS insulation limited lifetime warranty maintains 90% of its R-value for the lifetime of the building and covers all CAN/ULC-S701 properties. See FOAMULAR® NGX™ Extruded Polystyrene Insulation Lifetime Limited Warranty for complete details, limitations, and requirements.

Technical Services Available

For Canadian Technical inquiries please contact local representative. See Technical territory map via www.specowenscorning.ca/contacttech.

Current Ed: 2023.01.01
Previous Ed: 2022.12.01

OWENS CORNING CANADA LP
3450 MCNICOLL AVENUE
SCARBOROUGH, ONTARIO M1V 1Z5

1-800-GET-PINK®
www.owenscorning.ca

Pub. No. 501122H. Printed in Canada. January 2023.
THE PINK PANTHER™ & © 1964–2023 Metro-Goldwyn-Mayer Studios Inc.
All Rights Reserved. The colour PINK is a registered trademark of Owens Corning.
© 2023 Owens Corning. All Rights Reserved.